

NATIONAL TECHNICAL SYSTEMS

BALLISTIC RESISTANCE TEST

Date Received: August 21, 2023
 Via: Hand
 Returned Via: Hand

Record No.: SHD23003-13
 Test Date: October 9, 2023
 Customer: Safe Haven Defense

Test Conditions

Temperature: 72.8 F
 Humidity: 33 %
 Test Spec.: UL 752
 Test Reference: Table 3.1 ICW Paragraph 17.2.1
 Material Type: (Non-Metallic) Bullet Resisting Material
 Threat Level: Level 6
 Shots Required: 5

Range 3

Muzzle to Screen 1: 5.00 ft.
 Screen 1 - 2: 5.00 ft.
 Screen 2 - Target: 5.00 ft.
 Midpoint to Target: 7.50 ft.
 Target to Witness: 1.50 ft.
 Witness: 1/8" Corrugated Cardboard
 Barrel Length: 10 in.

Sample Description	Test / Ammunition Description					Chronograph		Test Result
Manufacturer: Safe Haven Defense Model No.: SW600BR Sample No.: N/A Size (in.): 18 x 18 Weight (lbs.): 17.110	Shot No.	Shot Location	Degree Obliquity	Caliber	Bullet Weight (gr.) /Type	TIME sx-5	VELOCITY ft/s	Penetration
	1	TL	0°			352.0	1420	No Penetration
	2	TR	0°			352.4	1419	No Penetration
	3	BR	0°	9mm	124 / FMJ	348.4	1435	No Penetration
	4	BL	0°			350.9	1425	No Penetration
	5	C	0°			349.2	1432	No Penetration

This test was performed in accordance with the specification requirements and the results properly reflect the ballistic performance of the listed sample.

National Technical Systems, Inc.
 7447 W. 33rd St. N.
 Wichita, KS 67205 U.S.A.

Phone: 316-832-1600

Notes:

•Sample secured to test fixture using frame and clamps.

Test Round Used:

Test Round: Remington 9mm, 124 gr. (8.0g) FMJ RN (23558)
 Test Velocity: 1400 - 1540 ft/s

Shot Locations / Spacing (17.2.1):

Shot Location: Center of Panel
 Shot Spacing: 5 Shot Dice Pattern
 Shot No. 1: Top Left
 Shot No. 2: Top Right
 Shot No. 3: Bottom Right
 Shot No. 4: Bottom Left
 Shot No. 5: Center

Sample Description:

Glass (2 x 0.250" thick w/ air gap).